

PURAFIL ENVIRONMENTAL CORROSION REPORT

14-Jun-2010

Company: 111037

Sales Order #: C002697
CCC Panel #: P67950
Date In: 21-May-2010
Date Out: 03-Jun-2010
Days In Service: 13

Room Area ID:
Reference #:



CCC Panel # P67950

ISA Class G2
Moderate

Copper Corrosion
380 Å/30 Days

Silver Corrosion
1554 Å/30 Days

(see next page for complete analysis)

Summary for PURAFIL CCC # P67950

The electrolytic reduction analysis on Corrosion Classification Coupon #P67950 shows the presence of moderate concentrations of contaminants in the environment tested. The hydrogen sulfide level is expected to range between 3 and 10 ppb and the sulfur dioxide level between 10 and 100 ppb. The effects of corrosion are measurable and may be a factor in determining equipment reliability.

Your local representative for additional information and assistance is:
 Environmental Health and Eng
 117 Fourth Avenue, Needham MA 02494, USA
 tminegishi@eheinc.com

Purafil, Inc. / 2654 Weaver Way, Doraville GA 30340 USA / (770) 662-8545 / (770) 263-6922
 Email: purafil@purafil.com / Internet: http://www.purafil.com

PURAFIL CCC # P67950 Analysis Results

Corrosion Film Composition				Gold Coupon - Magnified 20x
	Projections			
	<u>30 Days</u>	<u>1 Year</u>	<u>5 Year</u>	
Copper Films				
Cu ₂ S	0 Å	0 Å	0 Å	
Cu ₂ O	380 Å	501 Å	656 Å	
Unknowns	0 Å	0 Å	0 Å	
Totals	380 Å	501 Å	656 Å	
Silver Films				
AgCl	0 Å	0 Å	0 Å	
Ag ₂ S	1554 Å	18921 Å	94606 Å	
Unknowns	0 Å	0 Å	0 Å	
Totals	1554 Å	18921 Å	94606 Å	

Gold Pore Corrosion:
 Note: 1000 Å = 0.1 micron

Equipment Reliability Correlation
 (ISA Standard S71.04-1985 for Copper)

